


PL - White Cavitated (Label)



Key Performance Characteristics:

Cavitated white, two side treated, non heat sealable

Applications:

Inner ply of laminated roll-fed labels with clear BOPP overlamine

Technical Data

PROPERTIES	TEST METHOD	UNITS	TYPICAL VALUES			
			PL25	PL30	PL40	PL50
THICKNESS	Internal	mil (μm)	1.0 (25)	1.15 (29)	1.52 (39)	2.17 (55)
YIELD	Internal	in ² /lb (m ² /kg)	44,000 (62.5)	38,400 (54.6)	27,800 (39.5)	19,500 (27.7)
OPACITY	ASTM D589	%	76	82	88	93
TENSILE STRENGTH (MD/TD)	ASTM D882	lb/in ² (kg/cm ²)	10,000 / 20,000 (700) / (1,400)			
ELONGATION AT BREAK (MD/TD)	ASTM D882	%	110 / 50			
DIMENSIONAL STABILITY (MD/TD)	266°F (130°C) 5 min	%	<5 / <3			
SURFACE ENERGY (high energy side)	ASTM D2578	dyne/cm	38			
SURFACE ENERGY (lower energy side)	ASTM D2578	dyne/cm	36			

Revision Date: June 2017

The above properties and results obtained refer to the average values of laboratory testing carried out on sample Inteplast product. Inteplast does not guarantee testing accuracy and makes no guarantee of product performance, safety or suitability, either expressed or implied, when used alone or in combination with other products. Inteplast strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. Inteplast assumes no responsibility for any damage or injury sustained as a result of the use of its products.