

Inteplast Group
World-Pak Division
IntePlus[®] **Business Dept.**

TECHNICAL DATA SHEET
IntePlus[®]

Film Type: XF - VR

Property	Test Method	Unit	Film Direction	Typical Vaule	
Unit Weight (Nominal Thickness)	XFWI0201	GSM	--	250 ± 10%	350 ± 10%
		Mil	--	10.5 ± 10%	14.7 ± 10%
Tensile @ Ultimate	ASTM-D882	lbf/in	Avg.	50	63
Dart Impact	ASTM-D1709 (method A)	grams	--	--	--
	ASTM-D1709 (method B)			2400	2750
WVTR	ASTM E-96 (procedure B)	US Perms	--	0.040	0.029
Classification	ASTM E-1745	Class A,B,C	--	Exceeds	Exceeds

Please note that the above information is to the best of our knowledge and is made without guarantee. These are typical property values and are intended as guides only, not as specification limits. We can not anticipate all conditions under which this information and our products, or products of other manufacturers in combination with our products may be used. Users are advised to conduct their own test and evaluation to determine the safety and suitability for their own purposes. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products.

For additional information, call 1-800-452-2117, extension 8058.

Issued Date: 4/1/08